



## GEOPLÂTRE® N PLASTER



### Product description

Plaster from the gypsum of the Paris area, natural and fine, requiring a fast setting.

A specific product for finishing work on fire-protection structures, in combination with our pre-fabricated elements.

### Technical characteristics

Mixing rate :

P/E = 120-145/100%.

E/P = 80-69/100 %

Beginning of Vicat setting: 13 min

Expansion: 0.15%.

Compressive strength: 11 MPa

Granulometry at 200 µm : 0.8%.

### Implementation (in minutes)

Dusting: 1

Rest time: 1'

Mixing: 1-2'

Casting: 10-15'

Demoulding: 45-60'

### Packaging and storage

Keep in a dry place. Moisture absorption can alter the mechanical and physical properties of plasters. Open bags must be carefully closed between each use to protect the product.